

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-147074

(43)Date of publication of application : 21.05.2003

(51)Int.Cl.

C08G 65/38
C08J 5/18
// H01M 8/02
H01M 8/10
C08L 71:00

(21)Application number : 2001-351750

(71)Applicant : TOYOBO CO LTD

(22)Date of filing : 16.11.2001


(72)Inventor : SAKAGUCHI YOSHIMITSU
HAMAMOTO SHIRO
NAKAO JUNKO
TATEMORI HIROSHI
TAKASE SATOSHI

(54) AROMATIC POLYARYLENE ETHER COMPOUND CONTAINING SULFONIC ACID GROUP AND POLYMER ELECTROLYTE MEMBRANE

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a compound having excellent ionic conductivity, water- resistance and heat-resistance by controlling the amount of introduced sulfonic acid group and provide a resin composition of the compound and an ionic conductive film.

SOLUTION: The polyarylene ether compound having a sulfonic acid group contains a repeating unit expressed by formula (1) (Ar1 is a group of formula (3); Ar2 is a group of formula (4)) and a repeating unit expressed by formula (2) (Ar3 is a group expressed by either one of formulas (5a) to (5c); A is ketone group or sulfone group; B, C, D and E are each H, a 1-6C aliphatic group, nitro group, chlorine, bromine or iodine provided that at least two of B, C, D and E are H; and F is direct bond, sulfone group, ketone group, ether group or a 1-6C alkylidene group).



LEGAL STATUS

[Date of request for examination] 16.09.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

JAPANESE [JP,2003-147074,A]

CLAIMS DETAILED DESCRIPTION TECHNICAL FIELD PRIOR ART EFFECT OF THE
INVENTION TECHNICAL PROBLEM MEANS EXAMPLE DESCRIPTION OF DRAWINGS
DRAWINGS

[Translation done.]

* NOTICES *

JPO and NCIPI are not responsible for any damages caused by the use of this translation.


1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]


[Claim 1] The sulfonic group content aromatic series poly arylene ether compound characterized by including the repeating unit expressed with the following formula (1), and the repeating unit expressed with the following formula (2).

[Formula 1]




In [type (1), Ar1 shows the joint unit expressed with the following formula (3), and Ar2 shows the joint unit expressed with the following formula (4).]

[Formula 2]




In [type (2), Ar1 shows the joint unit expressed with the following formula (3), and Ar3 shows the joint unit expressed with the following formula (5a) - (5c) either.]

[Formula 3]



In [type (3), A shows a ketone group or a sulfone radical. B, C, D, and E are the aliphatic series radical containing hydrogen or 1-6 carbon, a nitro group, chlorine, a bromine, and iodine, and at least two sorts in B, C, D, and E consist of hydrogen.]




[Formula 4]



In [type (4), F shows direct coupling, a sulfone radical, a ketone group, a ether group, or the alkylidene radical of carbon numbers 1-6. B, C, D, and E are the aliphatic series radical containing hydrogen or 1-6

carbon, a nitro group, chlorine, a bromine, and iodine, and at least two sorts in B, C, D, and E consist of hydrogen.]

[Formula 5]



In [type (5a) - (5c), n_1 - n_{11} are the integers of 0-2, and any groups of $(n_1+n_2+n_3)$, $(n_4+n_5+n_6+n_7)$, and $(n_8+n_9+n_{10}+n_{11})$ are integers other than zero. Moreover, Substituent X is the alkyl group containing 1-3 carbon, the alkoxyl group containing 1-3 carbon, a hydroxyl group, the amino group, an acyl group, hydrogen, or a halogen, and m_s+n_s is an integer expressed with $0 \leq m_s+n_s \leq 5$ ($s = 1, 11$) or $0 \leq m_s+n_s \leq 4$ ($s = 2, 3, 4, 5, 6, 7, 9, 10$).]

[Claim 2] The sulfonic group content aromatic series poly arylene ether compound according to claim 1 characterized by the sulfonic group having combined with each one aromatic series ring of every in aforementioned formula (5a) - (5c).

[Claim 3] The sulfonic group content aromatic series poly arylene ether compound according to claim 1 or 2 characterized by including repeating units other than the repeating unit expressed with the aforementioned formula (1) or (2).

[Claim 4] A sulfonic group content aromatic series poly arylene ether compound given in either of claims 1-3 characterized by the sum total (1- α) of the mole ratio of repeating units other than the

repeating unit expressed with the sum total alpha of the mole ratio of a repeating unit expressed with the aforementioned formula (1) or (2), the aforementioned formula (1), or (2) filling the relation of $1 \leq \alpha / (1 - \alpha) \leq 99$.

[Claim 5] A sulfonic group content aromatic series poly arylene ether compound given in either of claims 1-4 to which mole-ratio beta of the repeating unit expressed with the aforementioned formula (1) and the mole ratio (1-beta) of the repeating unit expressed with the aforementioned formula (2) are characterized by filling the relation of $0.5 \leq \beta / (1 - \beta) \leq 10$.

[Claim 6] a logarithm -- a sulfonic group content aromatic series poly arylene ether compound given in either of claims 1-5 characterized by viscosity being 0.1 or more.

[Claim 7] The resin constituent characterized by the sulfonic group content aromatic series poly arylene ether compound given in either of claims 1-6 being mixed by resin.

[Claim 8] The resin constituent according to claim 7 characterized by under 100 mass % being constituted from a sulfonic group content aromatic series poly arylene ether compound of a publication more than 50 mass % of the whole resin constituent by either of claims 1-6.

[Claim 9] Polyelectrolyte film characterized by containing the compound of a publication in either of claims 1-6.

[Translation done.]


* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.


1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DRAWINGS


[Drawing 1]




[Drawing 2]




[Drawing 3]




[Drawing 4]




[Drawing 5]




[Drawing 6]



[Drawing 7]



[Drawing 8]



[Translation done.]